



Printed 4/11/2024

Z2346

TECHNICAL SERVICE BULLETIN

POLYCHEM[®] 7780-X-50

POLYCHEM[®] 7780-X-50 is a short-oil TOFA alkyd formulated for air dry and low bake / force dry industrial finishes.

<u>CHARACTERISTIC</u>	<u>SPECIFICATIONS</u>
NVM%	49 - 51
VISCOSITY, G-H	Z1 - Z3
POUNDS PER GALLON	8.3 +/- 0.1
ACID NUMBER (NVM)	14 MAX
GARDNER COLOR	6 MAX
REDUCED VISCOSITY	H - K
REDUCED NVM	40
REDUCED SOLVENT	Xylene
CLARITY	CLEAR

APPLICATIONS

Fast Air Dry / Force Dry Industrial Enamel
Primer & Shop Coats

DRIER RECOMMENDATIONS (% METAL ON TOAL BINDER SOLIDS):

Cobalt 0.03 - 0.05%
Zirconium 0.15 - 0.40%

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use, either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that all workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE,

Form Revision 04/01/16

Revision Date 2/22/2023

1920 LEONARD AVENUE COLUMBUS OH 43219
PHONE (614) 253-8511 EMAIL - info@opcpolymers.com