



## TECHNICAL SERVICE BULLETIN

### POLYCHEM® G2507-OMS-70

POLYCHEM® G2507-OMS-70 is a general purpose gloss air drying enamel vehicle with excellent resistance to yellowing on aging. This resin is designed for use in enamels where low V.O.C. is required.

<u>CHARACTERISTIC</u>	<u>SPECIFICATIONS</u>
NVM%	69 - 71
VISCOSITY, G-H	Z3 - Z5
SOLVENT	Odorless Mineral Spirits
POUNDS PER GALLON	8 +/- 0.1
ACID NUMBER (NVM)	14 MAX
GARDNER COLOR	8 MAX
REDUCED VISCOSITY	G - K
REDUCED NVM	50
REDUCED SOLVENT	Odorless Mineral Spirits
OIL	Soybean Oil
CLARITY	Clear

### APPLICATIONS

Used for high quality exterior gloss and trim enamels. Also used in many industrial finishes such as machinery enamels, freight and marine paints, etc.

### DRIER RECOMMENDATIONS (% METAL ON TOAL BINDER SOLIDS):

Air Dry:

25 C, 50% RH, 0.075 mm Wet

Tack Free 5-6 hrs.

Driers:

Cobalt 0.06%

Calcium 0.1%

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use, either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that all workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE,