



TECHNICAL SERVICE BULLETIN

POLYCHEM® G7758-MS16-60

POLYCHEM® G7758-MS16-60 is a general purpose air drying enamel vehicle with maximum resistance to yellowing on aging and exposure to kitchen fumes.

<u>CHARACTERISTIC</u>	<u>SPECIFICATIONS</u>
NVM%	59 - 61
VISCOSITY, G-H	Z1 - Z3
SOLVENT	Mineral Spirits 16
POUNDS PER GALLON	7.75 +/- 0.1
ACID NUMBER (NVM)	10 MAX
GARDNER COLOR	5 MAX
REDUCED VISCOSITY	N - R
REDUCED NVM	50
REDUCED SOLVENT	Mineral Spirits 16
OIL	Soybean Oil
CLARITY	CLEAR

APPLICATIONS

Use for high quality interior or exterior architectural gloss and trim enamels. Also for use in industrial finishes such as machinery enamels, freight and marine paints, etc.

DRIER RECOMMENDATIONS (% METAL ON TOAL BINDER SOLIDS):

Air Dry:

25 C, 50% RH, 3 mil Wet

Tack Free 5-6 hrs.

Driers:

Cobalt	0.04%
Zirconium	0.5%
Calcium	0.1%

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use, either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that all workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE,